CFS Connections



Max. grip

Strong-Drive PHSD FRAMING-TO-CFS Screw

Common Applications:

· Cold-formed steel framing and sheet-steel sheathing to cold-formed steel

Codes/Standards: ASTM C1513 compliant

For more information, see p. 237, C-F-2023 Fastening Systems catalog

length 4 -3/4"

PHSD Screw — Cold-Formed Steel Member Connection Loads, Steel to Steel

Size- TPI x Length		MANAGEM COMPA		Refe	rence Shea	r (lb.)	Refer	ence Pullove	er (lb.)	Reference Pullout (lb.)				
	Model No.	Nominal Dia. (in.)	Load Description	Steel T	hickness: [n	nil (ga.)]	Steel T	nickness: [m	nil (ga.)]	Steel Thickness: [mil (ga.)]				
				27 (22)	33 (20)	43 (18)	27 (22)	33 (20)	43 (18)	27 (22)	33 (20)	43 (18)		
#8-18 x ¾	PHSD34S0818	0.164	ASD load	181	235	305	220	345	390	67	125	133		
			LRFD load	290	375	490	350	550	620	107	200	213		
			Nominal strength	410	590	765	540	845	955	164	310	325		

- 1. Screws and screw connections have been tested per AISI Standard Test Method S904 and S905. This screw is not recommended for 16 gauge and thicker steel. Provide a 1/8" diameter predrilled hole in 16 gauge and thicker steel, if this screw should be used.
- 2. The tabulated ASD and LRFD allowable loads for cold-formed steel (CFS) members are based on the lower of the screw strength or the strength of the screw in the connected members per AISI S100.
- The safety factor is based on AISI S100-07.
- The average ultimate/nominal values listed should not be used for design loads.
- Values are based on CFS members with a minimum yield strength of Fy = 33 ksi and tensile strength of $F_U = 45$ ksi for 43 mil (18 ga.) to 27 mil (22 ga.), minimum yield strength of $F_Y = 50$ ksi and $F_U = 65$ ksi for 54 mil (16 ga.) to 97 mil (12 ga.).
- For design purposes, steel-sheet thicknesses are 0.0283" for 27 mil, 0.0346" for 33 mil, 0.0451" for 43 mil, 0.0566" for 54 mil, 0.0713" for 68 mil, and 0.1017" for 97 mil. The actual sheet thickness shall not be less than 95% of these design thicknesses as specified in AISI S100.

- 7. Screw diameters per AISI S200 General Provision Commentary Table D1.1.
- 8. Minimum required screw length is the lesser of 3/4" or the minimum length required for the screw to extend through the steel connection a minimum of three exposed threads per AISI S200 General Provisions Standard Section D1.3.
- Maximum grip length for the PHSD34S0818 is 0.40". Grip length is the total connection thickness plus three protruding threads.
- 10. Screw head or washer diameter, dw is 0.307".
- 11. The allowable load (ASD) values shown are not permitted to be increased for short-duration loads such as wind or earthquake loads
- 12. The lower of the pullover and pullout allowable load should be used for tension design.
- 13. The tabulated shear values are based on the thinner steel member in connection. Steel thickness for both members must be in the range of
- 14. See general load tables on p. 22 for screw strength.

Strong-Drive° FPHSD FRAMING-TO-CFS Screw

Common Application:

C-F-2023TECHSUP @ 2023 Simpson Strong-Tie Company Inc.

Cold-formed steel framing and sheet steel sheathing to cold-formed steel

Codes/Standards: ASTM C1513 compliant, ICC-ES ESR-3006

For more information, see p. 237, C-F-2023 Fastening Systems catalog

FPHSD — Cold-Formed Steel Member Connection Loads, Steel to Steel



Size- TPI x Length	Model No.	Nominal Dia. (in.)	Load Description	Reference Shear (lb.) Steel Thickness: [mil (ga.)]					Reference Pullover (lb.) Steel Thickness: [mil (ga.)]						Reference Pullout (lb.) Steel Thickness: [mil (ga.)]						
																					27 (22)
				#10-16 x ¾	FPHSD34S1016	0.190	ASD load	175	235	380	570	570	570	280	365	485	695	740	740	76	95
LRFD load	280	375	605				855	855	855	445	585	775	1,110	1,110	1,110	123	151	250	380	545	805
Nominal strength	395	535	860				1,305	1,305	1,305	685	895	1,190	1,705	2,215	2,215	190	230	385	585	840	1,235
#12-14 x ¾	FPHSD34S1214	0.216	ASD load	205	260	410	610	610	610	240	330	430	630	840	1,125	76	95	159	240	345	530
			LRFD load	330	420	650	975	975	975	390	530	685	1,005	1,340	1,690	123	151	255	385	550	855
			Nominal strength	485	610	930	1,385	1,385	1,385	595z	815	1,050	1,540	2,060	2,065	190	230	390	590	845	1,295

- Screws and connections have been tested per AISI Standard Method S904 and S905.
- The tabulated ASD and LRFD allowable loads for cold-formed steel (CFS) members are based on the lower of the screw strength or the strength of the screw in the connected members per AISI S100.
- Values are based on CFS members with a minimum yield strength of F_y = 33 ksi and tensile strength of $F_U=45$ ksi for 43 mil (18 ga.) to 27 mil (22 ga.), minimum yield strength of $F_Y=50$ ksi and $F_U=65$ ksi for 54 mil (16 ga.) to 97 mil (12 ga.).
- For design purposes, steel sheet thicknesses are 0.0283" for 27 mil, 0.0346" for 33 mil, 0.0451" for 43 mil, 0.0566" for 54 mil, 0.0713" for 68 mil, and 0.1017" for 97 mil. The actual sheet thickness shall not be less than 95% of these design thicknesses as specified in AISI S100.
- 5. Screw diameters per AISI S200 General Provision Commentary Table D1.1.
- Minimum required screw length is the lesser of 3/4" or the minimum length required for the screw to extend through the steel connection a minimum of three exposed threads per AISI S200 General Provisions Standard Section D1.3.

- Maximum grip length for the FPHSD34S1016 is 0.31". Maximum grip length for the FPHSD34S1214 is 0.28". Grip length is the total connection thickness plus three protruding threads.
- Screw head dw for #10 and #12 screws is 0.357".
- The allowable load (ASD) values shown are not permitted to be increased for short-duration loads such as wind or earthquake loads.
- 10. The lower of the pullover and pullout allowable load should be used for tension design.
- 11. The tabulated shear values are based on the thinner steel member in connection. Steel thickness for both members must be in the range of 12-22 gauge
- See the general load tables on p. 22 for screw strength.